



**Quicksilver® UHMW-PE Premium Truck Lining (ASTM Product Data Sheet)**

**Categories:** Polymer; Thermoplastic; Polyethylene (PE); High Density (HDPE); High Density Polyethylene (HDPE), UHMW PE Ultra High Molecular Weight

**Material Notes:** Quadrant Engineering Plastic Products is now MCAM

Physical Properties	Metric	English	Comments
Specific Gravity	0.930 g/cc	0.930 g/cc	ASTM D792
Water Absorption	<= 0.010 %	<= 0.010 %	Immersion, 24hr; ASTM D570(2)
Water Absorption at Saturation	<= 0.010 %	<= 0.010 %	Immersion; ASTM D570(2)

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	66	66	ASTM D2240
Tensile Strength	30.3 MPa	4400 psi	ASTM D638
Tensile Strength at 65°C (150°F)	2.76 MPa	400 psi	ASTM D638
Elongation at Break	230 %	230 %	ASTM D638
Tensile Modulus	0.483 GPa	70.0 ksi	ASTM D638
Flexural Strength	24.1 MPa	3500 psi	ASTM D790
Flexural Modulus	0.455 GPa	66.0 ksi	ASTM D790
Compressive Strength	20.7 MPa	3000 psi	10% Def.; ASTM D695
Compressive Modulus	0.552 GPa	80.0 ksi	ASTM D695
Shear Strength	33.1 MPa	4800 psi	ASTM D732
Izod Impact, Notched	NB	NB	ASTM D256 Type A
Coefficient of Friction, Dynamic	0.090	0.090	Dry vs. Steel; QTM55007
Sand Slurry	10	10	1018 Steel = 100; ASTM D4020
Limiting Pressure Velocity	0.0701 MPa-m/sec	2000 psi-ft/min	4:1 safety factor; QTM 55007

Electrical Properties	Metric	English	Comments
Surface Resistivity per Square	>= 1.00e+13 ohm	>= 1.00e+13 ohm	ASTM D257
Dielectric Constant	2.3 @Frequency 1e+6 Hz	2.3 @Frequency 1e+6 Hz	ASTM D150
Dielectric Strength	90.0 kV/mm	2290 kV/in	Short Term; ASTM D149
Dissipation Factor	<= 0.00050 @Frequency 1e+6 Hz	<= 0.00050 @Frequency 1e+6 Hz	ASTM D150

Thermal Properties	Metric	English	Comments
CTE, linear	198 µm/m-°C @ Temperature -40.0 - 149°C	110 µin/in-°F @ Temperature -40.0 - 300°F	ASTM E831
Melting Point	135 °C	275 °F	Crystalline, Peak; ASTM D3418
Maximum Service Temperature, Air	82.2 °C	180 °F	Long Term
Deflection Temperature at 1.8 MPa (264 psi)	46.7 °C	116 °F	ASTM D648
Flammability, UL94	HB @Thickness 3.17 mm	HB @Thickness 0.125 in	Estimated Rating

Compliance Properties	Metric	English	Comments
3A-Dairy	No	No	
Canada AG	No	No	
FDA	No	No	
NSF	No	No	
USDA	No	No	
USP Class VI	No	No	

Chemical Resistance Properties	Metric	English	Comments
Acids, Strong (pH 1-3)	Limited	Limited	
Acids, Weak	Acceptable	Acceptable	
Alcohols	Acceptable	Acceptable	
Alkalies, Strong (pH 11-14)	Acceptable	Acceptable	
Alkalies, Weak	Acceptable	Acceptable	
Chlorinated Solvents	Acceptable	Acceptable	
Conductive / Static Dissipative	No	No	
Continuous Sunlight	Acceptable	Acceptable	
Hot Water / Steam	Limited	Limited	
Hydrocarbons - Aliphatic	Acceptable	Acceptable	
Hydrocarbons - Aromatic	Unacceptable	Unacceptable	

Inorganic Salt Solutions	Acceptable	Acceptable
Ketones, Esters	Limited	Limited